



www.silexsc.com.pl

Silex
ul. Skłodowskiej 12
tel.: +48 68 385 2845
email: biuro@silexsc.com.pl

66-100 Sulechów
tel. kom.: +48 508 354 588
www.srubydozorowe.pl

Bolts chemical properties

Class properties	Material and treatment	Chemical constitution (inspection analysis) % (m/m)				Allowable temperature	
		C		P	S	B	°C
		min	max	max	max	max	min
3.6	Carbon steel	-	0,20	0,05	0,06	0,003	-
4.6		-	0,55	0,05	0,06	0,003	-
4.8							
5.6		0,13	0,55	0,05	0,06	0,003	-
5.8		-	0,55	0,05	0,06		
6.8							
8.8	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,15	0,40	0,035	0,035	0,003	425
	Carbon steel quenched and tempered	0,25	0,55	0,035	0,035		
9.8	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,15	0,35	0,035	0,035	0,003	425
	Carbon steel quenched and tempered	0,25	0,55	0,035	0,035		
10.9	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,15	0,35	0,035	0,035	0,003	340
10.9	Carbon steel quenched and tempered	0,25	0,55	0,035	0,035	0,003	425
	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,20	0,55	0,035	0,035		
	Carbon steel quenched and tempered	0,20	0,55	0,035	0,035		
12.9	Carbon steel quenched and tempered	0,28	0,50	0,035	0,035	0,003	380